

Data sheets for over **58,000** metals, plastics, ceramics, and composites.[Advertise with MatWeb!](#)[REGISTER NOW](#)[HOME](#) • [SEARCH](#) • [TOOLS](#) • [SUPPLIERS](#) • [FOLDERS](#) • [ABOUT US](#) • [FAQ](#) • [LOGIN](#)Searches: [Advanced](#) | [Material Type](#) | [Property](#) | [Composition](#) | [Trade Name](#) | [Manufacturer](#) [SEARCH](#)

Aluminum Anodizing

www.eastwestdye.com (800) 407-6371[Aluminum Anodizing - Hardcoating - 24 Hour Turnaround Available - Mil-Spec Certified - Custom Coloring](#)

Aluminum 7075-T6; 7075-T651

[Return to last search](#)[Printer friendly version](#)[Download to Excel \(requires Excel and Windows\)](#)[Export data to your CAD/FEA program](#)Add to Folder: [Material suppliers](#)**Subcategory:** 7000 Series Aluminum Alloy; Aluminum Alloy; Metal; Nonferrous Metal**Close Analogs:****Composition Notes:**

A Zr + Ti limit of 0.25 percent maximum may be used with this alloy designation for extruded and forged products only, but only when the supplier or producer and the purchaser have mutually so agreed. Agreement may be indicated, for example, by reference to a standard, by letter, by order note, or other means which allow the Zr + Ti limit. Aluminum content reported is calculated as remainder.

Composition information provided by the Aluminum Association and is not for design.

Key Words: Aluminium 7075-T6; Aluminium 7075-T651, UNS A97075; ISO AlZn5.5MgCu; Aluminium 7075-T6; Aluminium 7075-T651; AA7075-T6

Component	Wt. %	Component	Wt. %	Component	Wt. %
Al	87.1 - 91.4	Mg	2.1 - 2.9	Si	Max 0.4
Cr	0.18 - 0.28	Mn	Max 0.3	Ti	Max 0.2
Cu	1.2 - 2	Other, each	Max 0.05	Zn	5.1 - 6.1
Fe	Max 0.5	Other, total	Max 0.15		

Material Notes:

General 7075 characteristics and uses (from Alcoa): Very high strength material used for highly stressed structural parts. The T7351 temper offers improved stress-corrosion cracking resistance.

Applications: Aircraft fittings, gears and shafts, fuse parts, meter shafts and gears, missile parts, regulating valve parts, worm gears, keys, aircraft, aerospace and defense applications; bike frames, all terrain vehicle (ATV) sprockets.

Data points with the AA note have been provided by the Aluminum Association, Inc. and are NOT FOR DESIGN.

[Click here to view available vendors for this material.](#)

Physical Properties	Metric	English	Comments
Density	2.81 g/cc	0.102 lb/in ³	AA; Typical
Mechanical Properties			
Hardness, Brinell	150	150	AA; Typical; 500 g load; 10 mm ball
Hardness, Knoop	191	191	Converted from Brinell Hardness Value
Hardness, Rockwell A	53.5	53.5	Converted from Brinell Hardness Value
Hardness, Rockwell B	87	87	Converted from Brinell Hardness Value
Hardness, Vickers	175	175	Converted from Brinell Hardness Value
Ultimate Tensile Strength	572 MPa	83000 psi	AA; Typical
Tensile Yield Strength	503 MPa	73000 psi	AA; Typical
Elongation at Break	11 %	11 %	AA; Typical; 1/16 in. (1.6 mm) Thickness
Elongation at Break	11 %	11 %	AA; Typical; 1/2 in. (12.7 mm) Diameter
Modulus of Elasticity	71.7 GPa	10400 ksi	AA; Typical; Average of tension and compression. Compression modulus is about 2% greater than tensile modulus.
Poisson's Ratio	0.33	0.33	
Fatigue Strength	159 MPa	23000 psi	AA; 500,000,000 cycles completely reversed stress; RR Moore machine/specimen
Fracture Toughness	20 MPa-m^{1/2}	18.2 ksi-in ^{1/2}	K(IC) in S-L Direction
Fracture Toughness	25 MPa-m^{1/2}	22.8 ksi-in ^{1/2}	K(IC) in T-L Direction
Fracture Toughness	29 MPa-m^{1/2}	26.4 ksi-in ^{1/2}	K(IC) in L-T Direction
Machinability	70 %	70 %	0-100 Scale of Aluminum Alloys
Shear Modulus	26.9 GPa	3900 ksi	
Shear Strength	331 MPa	48000 psi	AA; Typical
Electrical Properties			
Electrical Resistivity	5.15e-006 ohm-cm	5.15e-006 ohm-cm	AA; Typical at 68 °F

Thermal Properties

CTE, linear 68°F	23.6 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	13.1 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	AA; Typical; Average over 68-212°F range.
CTE, linear 250°C	25.2 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	14 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	Average over the range 20-300°C
Specific Heat Capacity	0.96 J/g-°C	0.229 BTU/lb-°F	
Thermal Conductivity	130 W/m-K	900 BTU-in/hr-ft ² -°F	AA; Typical at 77°F
Melting Point	477 - 635 °C	890 - 1175 °F	AA; Typical range based on typical composition for wrought products 1/4 inch thickness or greater. Homogenization may raise eutectic melting temperature 20-40°F but usually does not eliminate eutectic melting.
Solidus	477 °C	890 °F	AA; Typical
Liquidus	635 °C	1175 °F	AA; Typical

Processing Properties

Annealing Temperature	413 °C	775 °F
Solution Temperature	466 - 482 °C	870 - 900 °F
Aging Temperature	121 °C	250 °F

 [Printer friendly version](#)
References for this datasheet.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's disclaimer and terms of use regarding this information. [Click here](#) to view all the property values for this datasheet as they were originally entered into MatWeb.

**Aluminum Anodizing**
www.eastwestdye.com (800) 407-6371

[Aluminum Anodizing - Hardcoating - 24 Hour Turnaround Available - Mil-Spec Certified - Custom Coloring](#)
Subscribe to Premium Services
Searches: [Advanced](#) • [Composition](#) • [Property](#) • [Material Type](#) • [Manufacturer](#) • [Trade Name](#) • [UNS Number](#)
Other Links: [Advertising](#) • [Submit Data](#) • [Database Licensing](#) • [Web Design & Hosting](#) • [Trade Publications](#)
[Supplier List](#) • [Unit Converter](#) • [Reference](#) • [News](#) • [Links](#) • [Help](#) • [Contact Us](#) • [Site Map](#) • [FAQ](#) • [Home](#)

Please read our [License Agreement](#) regarding materials data and our [Privacy Policy](#). Questions or comments about MatWeb? Please contact us at webmaster@matweb.com. We appreciate your input.

Site designed and maintained by Automation Creations, Inc. The contents of this web site, the MatWeb logo, and "MatWeb" are Copyright 1996-2006 by Automation Creations, Inc. MatWeb is intended for personal, non-commercial use. The contents, results, and technical data from this site may not be reproduced either electronically, photographically or substantively without permission from Automation Creations, Inc.